

# Dissolution kinetics of AFm-Cl as a function of pH at room temperature.

Nicolas Marty, Sylvain Grangeon

► **To cite this version:**

Nicolas Marty, Sylvain Grangeon. Dissolution kinetics of AFm-Cl as a function of pH at room temperature.. 14ème Colloque du Groupe Français des Argiles, May 2016, Poitier, France. 2016. hal-01293219

**HAL Id: hal-01293219**

**<https://hal-brgm.archives-ouvertes.fr/hal-01293219>**

Submitted on 24 Mar 2016

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Dissolution kinetics of AFm-Cl as a function of pH at room temperature.

N.C.M. Marty & S. Grangeon<sup>1</sup>

<sup>1</sup>*BRGM, 3 avenue Claude Guillemin, 45060 Orléans cedex 2, France*

E-mail: [n.marty@brgm.fr](mailto:n.marty@brgm.fr)

Estimation of reliable weathering/dissolution rates of cement phases is of fundamental importance for modelling the temporal evolution of radioactive waste repositories and well for CO<sub>2</sub> geological storage. In this context dissolution kinetics of AFm (hydrated calcium aluminates) have been studied with flow-through experiments at pH ranging from 9.2 to 13. Dissolution kinetics of a pure AFm-Cl, i.e. a mix between the Friedel's salt and its naturally-occurring form, hydrocalumite, have been investigated. Mineralogical (XRD) and chemical (EPMA, TEM/EDX) analyses have been performed to characterize the reacting minerals prior and after dissolution experiments.

For pH values ranging from 10 to 13, flow-through experiments indicate congruent dissolutions of AFm-Cl (i.e. Ca/Al ratios close to 2 both for solids and outlet concentrations). In contrast a precipitation of Al-phases and mixed Al/Ca phases are expected at pH 9.2 leading to high Ca/Al ratios of outlet solutions. However, estimated rate in such condition appears to be weakly affected by these secondary-phase formations. Accordingly, far-from-equilibrium dissolution rates were normalized to the final specific surface areas (ranging from 6.1 to 35.4 m<sup>2</sup> g<sup>-1</sup>). None significant effect of pH on dissolution kinetics can be draw and therefore the far-from-equilibrium dissolution kinetics at pH ranging from 9.2 to 13 and room temperature is expressed as:

$$\log R(\text{mol m}^{-2} \text{ s}^{-1}) = -9.23 \pm 0.18$$