



HAL
open science

TUNGSTEN RECOVERY FROM SULFIDE-CONTAINING W-TAILINGS: Beneficiation Tests and Bioleaching for Sulphide Removal

Douglas O. Pino-Herrera, Solène Touzé, Anne-Gwenaëlle Guezennec,
Françoise Bodénan

► **To cite this version:**

Douglas O. Pino-Herrera, Solène Touzé, Anne-Gwenaëlle Guezennec, Françoise Bodénan. TUNGSTEN RECOVERY FROM SULFIDE-CONTAINING W-TAILINGS: Beneficiation Tests and Bioleaching for Sulphide Removal. 18ème congrès de la Société Française de Génie des Procédés, Nov 2022, Toulouse, France. hal-03926560

HAL Id: hal-03926560

<https://hal-brgm.archives-ouvertes.fr/hal-03926560>

Submitted on 6 Jan 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

TUNGSTEN RECOVERY FROM SULFIDE-CONTAINING W-TAILINGS: Beneficiation Tests and Bioleaching for Sulphide Removal

Douglas PINO-HERRERA¹, Solène TOUZE¹, Anne-Gwénaëlle GUEZENNEC¹, Françoise BODENAN¹

¹ BRGM, Water, Environment, Process and Analysis Division, 3 Avenue Claude Guillemin, BP36009, Orléans 45060, Cedex 2, France

Recovery of W-tailings

In the frame of the H2020 RAWMINA project (Grant Agreement n° 958252), recovery of critical raw materials such as tungsten (W) in mining waste is evaluated by various innovative (bio)hydrometallurgy techniques. First, the recovery of W from sulfidic mining waste is carried out by applying gravimetric separation techniques to concentrate W-bearing minerals (mainly scheelite). W can then be leached from the beneficiated tailings using alkaline leaching. However, arsenic-containing sulfides, such as arsenopyrite, can also be significantly deported in the W concentrate which can cause an increase of the reagents consumption in the alkaline leaching process (Suess and Planer-Friedrich, 2012). Moreover, the presence of As in the concentrate could negatively impact downstream processes and the final products. Bioleaching is known to be efficient in the removal of sulfidic material even at low sulfide content (Hubau et al., 2020). Therefore, after the beneficiation process, bioleaching is used to treat sulfide and reduce acidity, iron and arsenic concentrations in the beneficiated material.

Beneficiation of W-tailings by gravimetric methods

A representative sample (500 kg) was sampled on a mine site in Portugal and prepared at BRGM facilities to obtain homogenized sub-samples according to well-established procedures, i.e. drying, crushing, grinding and splitting. Beneficiation tests have been performed by gravimetric separation taking advantage of scheelite density (CaWO_3 , 5.9-6.1 g/cm³). This process can also concentrate the pyritic material (mainly constituted by arsenopyrite that have a similar density as scheelite). The first pre-treatment step was the classification in four size fractions (< 100 μm ; 100 μm – 250 μm ; 250 μm - 500 μm ; 500 μm - 1 mm), since scheelite was observed at particle size up to 1 mm by UV shortwave radiation (blue spots of scheelite bright fluorescence). Then, a separation step was carried out using a gravimetric Wilfley shaking table for the coarser fractions (Figure 1). W content in the beneficiated product quantified by portable XRF technology was increased by 10 fold (from around 2000 ppm to 2-5 wt. %). Concentration using Mozley Multi Gravity Separator (MGS) is also planned to treat fine fraction (< 100 μm). In addition, iron and sulfur content in the beneficiated samples have been increased, indicating that arsenopyrite (main sulfide contained in the tailings) has also been concentrated.



Figure 1: Beneficiation tests of W-tailings using a gravimetric Wilfley shaking table

Bioleaching of the beneficiated W-tailings

Bioleaching tests are currently being performed in shake flasks to adapt a selected acidophilic microbial consortium to the bioleaching of the sulfide contained in the beneficiated W-tailings. The next steps include the inoculation of 2-L reactors with the adapted microbial consortium and a progressive increase of the solid concentration in stirred tank reactors to bioleach sulfides and produce sulfide-free samples. Preliminary bioleaching tests show that this substrate is particularly suitable for the growth and the activity of S- and Fe-oxidizing activity. The dissolution of sulfide minerals (mainly arsenopyrite) is almost complete and leads to the production of a solution of sulfuric acid and ferric iron.

Conclusion and perspectives

The beneficiation process applied to the W-tailings allowed concentrating not only scheelite but also arsenopyrite in the W-tailings. An optimal flowsheet of beneficiation and bioleaching processes will be established as a pretreatment of the tailings before alkaline leaching to dissolve tungsten. Downstream process considered in RAWMINA project include the W selective recovery using nanofibrous composite materials and electrowinning. Finally, the overall RAWMINA process would allow the reprocessing of the W-tailings, recovering the remaining W and reducing the environmental risks associated with sulfide- and arsenic-containing mining residues.

References

Hubau, A.; Guezennec, A.-G.; Joulain, C.; Falagán, C.; Dew, D.; Hudson-Edwards, K.A., Bioleaching to reprocess sulfidic polymetallic primary mining residues : Determination of metal leaching mechanisms. *Hydrometallurgy* 2020, 197, 105484.

Suess, E.; Planer-Friedrich, B., Thioarsenate formation upon dissolution of orpiment and arsenopyrite. *Chemosphere* 2012, 89, 1390-1398.